GVT/PGVT




6335 MULTI CARRARA

(2 Surfaces & 5 Faces)



Coordinated Mosaics





Available Colors



6335 MULTI CARRARA



TECHNICAL SPECIFICATION

President Ceramic									
SR.NO	CHARACTERISTICS	TEST METHOD	STANDARDS AS PER ISO-13006;2013 GROUP Bla	OUR GENERAL TECHNICAL STANDARDS FOR POLISHED	OUR GENERAL TECHNICAL STANDARDS FOR SFS				
Α	DIMENSION & SURFACE QUALITY								
1	Deviation in length & width	ISO-10545-2	±0.5 %	± 0.3 %	± 0.3 %				
2	Deviation in thickness	ISO-10545-2	±5.0 %	±5.0%	±5.0%				
3	Straightness of side	ISO-10545-2	±0.5 %	± 0.5%	± 0.5%				
4	Rectangularity	ISO-10545-2	±0.6 %	± 0.35 %	± 0.35 %				
5	Surface flatness	ISO-10545-2	±0.5 %	± 0.40 %	± 0.40 %				
6	Surface quality	ISO-10545-2	95% OF the tiles free from visible defect	95%	95%				

В	PHYSICAL PROPERTIES				
1	Water absorption	ISO-10545-3	≤ 0.5%	≤ 0.5%	≤ 0.5%
2	Modulus of rupture	ISO-10545-4	> 35 N/MM²	> 35 N/MM ²	> 35 N/MM ²
3	Flexure breaking strength	ISO-10545-4	> 1300n	2000n	2000n
4	Moisture expansion	ISO-10545-10	0.02%	nil	nil
5	Scratch hardness (moh's)	ISO-10545-13	min-5	5*	5*
6	Resistance of surface abrasion	ISO-10545-7	PEI class ii min,	PEI class III	PEI class iV
7	Thermal expansion	ISO-10545-8	6x10 ⁻⁶ k ⁻¹	6.5x10 ⁻⁴ k ⁻¹	6.5x10 ⁻⁴ k ⁻¹
8	Thermal shock resistance	ISO-10545-9	min 10 cycle	10 cycle passed	10 cycle passed
9	Frost resistance	ISO-10545-12	no damage	no damage	no damage
10	Glossiness (Only for Polished Surface)	gloss meter	as per mfg.norms	≥90°	-

product. We reserve the rights to amend or delete either totally or partially, the sizes, references and other techanical specifications contained in the table above









































The President Group

At, Trajpar, 8-A, National Highway, Old Ghuntu Road, Morbi-363642. Contact: +91 9023 920 621 Email: Export@thepresidentgroup.com



For more sizes log in to : www.presidentceramic.com www.thepresidentgroup.com







